

## Typical Physical Properties

Physical Properties	Test Method	Unit	Typical Physical Properties
Nominal Density	ASTM D3575-08 Suffix W ISO 845:2006	Kg/m <sup>3</sup>	21
Compressive Strength Vertical @ 25% Vertical @ 50%	ASTM D3575-08 Suffix D ISO 7214:2007	KPa	7 12
Compressive Strength 25% (4th compression) 50% (4th compression) 70% (4th compression) (100mm/min compression speed)	ISO 3386 1986 part 1 DIN 53577	KPa	3 7 25
Compression Set	ASTM D3575-08 Suffix B (50% Compression)	%	< 30
	ISO 1856:2000 (25% compression)		< 20
Cell Size	BS 4443/1 Met.4	Cells/25mm	< 10
Fire-test-response Characteristics (1) Transportation Automotive	NF F 16-101 DIN 54837 FMVSS 302	Class Class -	F1 S3, SR2, ST2 Pass
Appliances & Electronics Building & Construction	UL94 DIN 4102 EN 13501-1	Class Class Class	HF1 B1 Class B-s1-d0
Water Pick Up by Diffusion (RH > 95% - after 28 days)	UNI EN 12088	Kg/m <sup>2</sup>	< 3
Water Pick Up by Diffusion (RH > 95% - after 28 days)	UNI EN 12088	Volume %	< 4
Thermal Conductivity @ 23°C @ -5°C	ASTM D3575-08 Suffix V ISO 8301	W/mK	0.104 0.082
Thermal stability (24hrs at 70°C)	ASTM D3575-08 Suffix S ISO 2796	%	< 3
Tensile Strength @ Peak	ASTM D3575 Suffix T ISO1798	KPa	130
Tensile Elongation	ASTM D3575 Suffix T ISO1798	%	60

(1) These numerical laboratory fire-test-response characteristics are not intended to reflect hazards presented by this material under actual fire conditions.

**NOTICE:** The data presented for this product is for unfabricated polyethylene foam product. While values shown are typical of this product, they should not be construed as specification limits. Sealed Air makes no warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, with respect to product, information or recommendations referred to herein, and shall not be liable for any loss or damage, directly or indirectly, related to such product, information or recommendations or for consequential or incidental damages. User should test each application to determine suitability of the product for the intended use.