

GERANIO.PB 15 POR.FINE

TECHNICAL DATA

Elastomer basis	NR
Hardness	soft
Delivery form	Blocks and manufactures parts
Max. Dimensions of blocks	mm.1150x890 - mm.1900x920 xy +/- mm.20
Cell structure	medium pore
Colour	orange
Compressive strength	approx. 4.8 kPa
Tensile strength	approx. 0.23 N / mm ²
Elongation at break	approx. 480 %
Continued tensile strength	approx. 1.2 N / mm
Abrasion resistance	good
Heat resistance	up to 60 – 70 °C
Cold resistance at – 40 °C	requirements fulfilled
Water absorption	approx. 484 weight %
Ozone resistance	not resistant
Flammability	highly flammable, burns with sooting
Stability	not resistant towards acids, alkalis, oils and fats and solvents. In doubt contact with manufacturing works is necessary.

The tests of compressive strength and compression set as well as the tension test give some information about the resistance of the quality.

We reserve the right to certain variations in respect of porosity, pore type, colour and plasticity as well as to changes which arise on the basis of production processes.

Environmental information:

Our sponge rubber materials do not contain ASBESTOS, FCCH, FORMALDEHYDE or heavy metals.
Only raw materials common to the rubber industry are used in the production of the mixtures.

GERANIO.PB 15 POR.MEDIA

TECHNICAL DATA

Elastomer basis	NR
Hardness	soft
Delivery form	Blocks and manufactures parts
Max. Dimensions of sheets	mm.1150x890 - mm.1900x920 xy +/- mm.20
Cell structure	medium pore
Colour	orange
Compressive strength	approx. 4.8 kPa
Tensile strength	approx. 0.23 N / mm ²
Elongation at break	approx. 480 %
Continued tensile strength	approx. 1.2 N / mm
Abrasion resistance	good
Heat resistance	up to 60 – 70 °C
Cold resistance at – 40 °C	at – 40 °C requirements fulfilled
Water absorption	approx. 484 weight %
Ozone resistance	not resistant
Flammability	highly flammable, burns with sooting
Stability	not resistant towards acids, alkalis, oils and fats and solvents. In doubt contact with manufacturing works is necessary.

The tests of compressive strength and compression set as well as the tension test give some information about the resistance of the quality.

We reserve the right to certain variations in respect of porosity, pore type, colour and plasticity as well as to changes which arise on the basis of production processes.

Environmental information:

Our sponge rubber materials do not contain ASBESTOS, FCCH, FORMALDEHYDE or heavy metals.

Only raw materials common to the rubber industry are used in the production of the mixtures.

GERANIO.PB 20 POR.FINE

TECHNICAL DATA

Elastomer basis	NR
Hardness	soft
Delivery form	Blocks and manufactures parts
Max. Dimensions of sheets	mm.1150x890 - mm.1900x920 xy +/- mm.20
Cell structure	fine pore
Colour	orange
Compressive strength	approx. 8,3 kPa
Tensile strength	approx. 0.22 N / mm ²
Elongation at break	approx. 495 %
Continued tensile strength	approx. 1.1 N / mm
Abrasion resistance	good
Heat resistance	up to 60 – 70 °C
Cold resistance at – 40 °C	requirements fulfilled
Water absorption	approx. 485 weight %
Ozone resistance	not resistant
Flammability	highly flammable, burns with sooting
Stability	not resistant towards acids, alkalis, oils and fats and solvents. In doubt contact with manufacturing works is necessary.

The tests of compressive strength and compression set as well as the tension test give some information about the resistance of the quality.

We reserve the right to certain variations in respect of porosity, pore type, colour and plasticity as well as to changes which arise on the basis of production processes.

Environmental information:

Our sponge rubber materials do not contain ASBESTOS, FCCH, FORMALDEHYDE or heavy metals.

Only raw materials common to the rubber industry are used in the production of the mixtures.

GERANIO.PB 20 POR.MEDIA

TECHNICAL DATA

Elastomer basis	NR
Hardness	medium
Delivery form	Blocks and manufactures parts
Max. Dimensions of sheets	mm.1150x890 - mm.1900x920 xy +/- mm.20
Cell structure	medium pore
Colour	orange
Compressive strength	approx. 8,3 kPa
Tensile strength	approx. 0.22 N / mm ²
Elongation at break	approx. 495 %
Continued tensile strength	approx. 1.1 N / mm
Abrasion resistance	good
Heat resistance	up to 60 – 70 °C
Cold resistance at – 40 °C	requirements fulfilled
Water absorption	approx. 485 weight %
Ozone resistance	not resistant
Flammability	highly flammable, burns with sooting
Stability	not resistant towards acids, alkalis, oils and fats and solvents. In doubt contact with manufacturing works is necessary.

The tests of compressive strength and compression set as well as the tension test give some information about the resistance of the quality.

We reserve the right to certain variations in respect of porosity, pore type, colour and plasticity as well as to changes which arise on the basis of production processes.

Environmental information:

Our sponge rubber materials do not contain ASBESTOS, FCCH, FORMALDEHYDE or heavy metals.

Only raw materials common to the rubber industry are used in the production of the mixtures.

GERANIO.PB 25 POR.FINE

TECHNICAL DATA

Elastomer basis	NR
Hardness	firm
Delivery form	Blocks and manufactures parts
Max. Dimensions of sheets	mm.1150x890 - mm.1900x920 xy +/- mm.20
Cell structure	fine pore
Colour	orange
Compressive strength	approx. 25 kPa
Tensile strength	approx. 0.33 N / mm ²
Elongation at break	approx. 460 %
Continued tensile strength	approx. 1.5 N / mm
Abrasion resistance	good
Heat resistance	up to 60 – 70 °C
Cold resistance at – 40 °C	requirements fulfilled
Water absorption	approx. 140 weight %
Ozone resistance	not resistant
Flammability	highly flammable, burns with sooting
Stability	not resistant towards acids, alkalis, oils and fats and solvents. In doubt contact with manufacturing works is necessary.

The tests of compressive strength and compression set as well as the tension test give some information about the resistance of the quality.

We reserve the right to certain variations in respect of porosity, pore type, colour and plasticity as well as to changes which arise on the basis of production processes.

Environmental information:

Our sponge rubber materials do not contain ASBESTOS, FCCH, FORMALDEHYDE or heavy metals.

Only raw materials common to the rubber industry are used in the production of the mixtures.

GERANIO.PB 30 POR.FINE

TECHNICAL DATA

Elastomer basis	NR
Hardness	very firm
Delivery form	Blocks and manufactures parts
Max. Dimensions of sheets	mm.1150x890 - mm.1900x920 xy +/- mm.20
Cell structure	fine pore
Colour	orange
Compressive strength	approx. 31 kPa
Tensile strength	approx. 0.54 N / mm ²
Elongation at break	approx. 480 %
Continued tensile strength	approx. 2.5 N / mm
Abrasion resistance	good
Heat resistance	up to 60 – 70 °C
Cold resistance at – 40 °C	requirements fulfilled
Water absorption	approx. 37 weight %
Ozone resistance	not resistant
Flammability	highly flammable, burns with sooting
Stability	not resistant towards acids, alkalis, oils and fats and solvents. In doubt contact with manufacturing works is necessary.

The tests of compressive strength and compression set as well as the tension test give some information about the resistance of the quality.

We reserve the right to certain variations in respect of porosity, pore type, colour and plasticity as well as to changes which arise on the basis of production processes.

Environmental information:

Our sponge rubber materials do not contain ASBESTOS, FCCH, FORMALDEHYDE or heavy metals.

Only raw materials common to the rubber industry are used in the production of the mixtures.